

ADVA[®] 108

New polymer-based superplasticiser for high performance, high durability concrete

Product Description

ADVA[®]108 is a new superplasticiser based on the polycarboxylate ether polymer technology. ADVA 108 superplasticiser is specially formulated to produce high workability, high slump, flowing concrete with enhanced strength and durability. ADVA 108 contains no added chloride and complies with the following specifications for chemical admixtures for concrete: BS 5075: Part 3; JIS A 6204, EN934-2: 2001. One litre weighs approximately 1.05kg ± 0.02kg.

Dispersion

Based on new comb polymer technology, ADVA 108 is a superior dispersing admixture having a marked capacity to disperse the cement agglomerates normally found in a cement-water suspension. Unlike conventional superplasticisers, which partially rely on electrostatic charge repulsive forces, ADVA 108 efficiently disperses cement particles using a powerful steric repulsion model. This allows for lower dosages and better control.

Product Advantages

- Long slump life with controlled retardation.
- Finishes easily without stickiness, tearing or spotty set characteristics.
- High slump concrete less susceptible to segregation and bleeding.
- Highly efficient in producing high slump concrete with no loss in strength.
- Easily added with the concrete mix water for rapid batching.

Compatibility with Other Admixtures

In concrete containing ADVA 108 the use of an air-entraining agent (such as DARAVAIR[®] or DAREX[®]AEA[®]) is recommended to provide suitable air void parameters for resistance against freeze-thaw attack. Due to synergistic effects between ADVA 108 and air-entraining agents, the quantity of air-entraining admixture added to concrete containing ADVA 108 may be reduced. Please consult your GCP representative for dosage guidance.

Most water reducers or water-reducing retarders are compatible with ADVA 108 Superplasticiser as long as they are added separately to the concrete

Caution should be exercised when using ADVA 108 with a retarder, as excessive retardation can occur if the admixture dosages are too high. Pre-testing of the concrete should be performed to optimise dosages and addition times of these admixtures. The admixtures should not be in contact with each other before they enter the concrete.

Dispensing Equipment

Please contact your local GCP representative for further information regarding the dispensing equipment for this product.



Applications

ADVA 108 produces concrete with extreme workability characteristics for high slump, flowing concrete. It also allows concrete to be produced with very low water-cement ratios at low or normal slumps. ADVA 108 is ideal for use in any concrete where it is desired to keep the water-cement ratio to a minimum and still achieve the degree of workability necessary to provide easy placement and consolidation. The addition of ADVA 108 will also fluidise concrete making it ideal for tremie concreting or other applications where high slumps are desired.

Addition Rates

Depending on the application, dosage rates can range from 200 to 2,000mL / 100kg of cementitious material. However, in most superplasticiser applications, 800 to 1,200mL / 100kg of cementitious material will be sufficient. For best results, ADVA 108 should be added with the mix water. At a given water-cement ratio, the slump required for placement can be controlled by varying the addition rate. Should job site conditions require using more than recommended addition rates, please consult your local GCP representative.

Packaging

ADVA 108 is available in bulk and in 205L drums. ADVA 108 contains no flammable ingredients. It will begin to freeze at approximately 0°C, but will return to full strength after thawing and thorough agitation.

It storage, and for proper dispensing, ADVA 108 should be maintained at temperatures above 0°C.

Health and Safety

See ADVA 108 Material Safety Data Sheet or consult GCP Applied Technologies.

gcpat.hk | For technical information: asia.enq@gcpat.com

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

ADVA, Daravair, Darex and AEA are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2017 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP (Hong Kong) Ltd., 6 On Chuen Street, On Lok Tsuen Ind Area, Fanling, Hong Kong

This document is only current as of the last updated date stated below and is valid only for use in Hong Kong. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.hk. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2025-05-15

gcpat.hk/solutions/products/adva-high-range-water-reducers/adva-108