

# Monokote<sup>®</sup> Z-156T

Ultra high density, cementitious fireproofing for tunnels and severe environmental exposure

---

## Product Description

Monokote<sup>®</sup>Z-156T ultra high density cementitious fireproofing has been developed by GCP Applied Technologies to meet specialty and industrial fireproofing requirements requiring greater resistance to harsh environmental conditions.

Monokote Z-156T is a Portland cement-based, factory-mixed material requiring only the addition of water on the job site for application. It is spray applied, providing up to 4 hours of fire resistance. Its physical characteristics are excellent for areas exposed to environmental or climatic conditions.

Monokote Z-156T may be used in areas where high durability and corrosion resistance is required such as substrates subjected to exterior exposure.

## Approvals

- Up to 4 hours in accordance with the Rijkswaterstaat (RWS) fire curve
- Up to 4 hours in accordance with UL 1709 hydrocarbon test
- Jet fire testing in accordance with HSE standard OTI 95 634
- Up to 4 hours in accordance with UL 263 (ASTM E119)
- Investigated by UL for exterior use

## Features & Benefits

Monokote Z-156T offers the following advantages to architects, engineers, and applicators:

- **Factory pre-mixed** - Ready to use. No job site proportioning required. Simply add water in a standard paddle-type plaster mixer and apply with conventional plastering equipment.
- **Non-toxic** - The factory-mixed blend of common Portland cement and other inert materials requires only the addition of water for mixing and application.
- **Attractive finishes** - Monokote Z-156T may be sprayed or hand troweled after spraying to achieve a lightly textured appearance.
- **Equipment versatility** - Monokote Z-156T can be mixed in a standard plaster mixer. After mixing, Monokote Z-156T may be spray-applied with commonly available pumping and spraying equipment.
- **Corrosion inhibition** - Monokote Z-156T neither prevents nor promotes the corrosion of steel, however, the inclusion of calcium nitrite as a corrosion inhibitor has been shown to retard the rate of corrosion due to salt and other aggressive environmental conditions.
- **Moisture resistant** - The Portland cement base affords excellent fire protection characteristics in areas subjected to high humidity.
- **Durable** - Hardness and maximum durability help resist accidental physical damage even in the toughest exposures.
- **Weatherable** - Able to withstand freeze/thaw, wind, rain and other climatic conditions.

## Uses

Monokote Z-156T may be used in roadway tunnels and in exterior environments where a highly durable fireproofing is required and a threat of steel corrosion is present.

## Delivery & Storage

All material to be used for fireproofing should be delivered in original unopened packages bearing the name of the manufacturer, the brand and proper Underwriters Laboratories Inc. labels for fire hazard and fire resistance classifications.

The material should be kept dry until ready for use. Keep packages of material off the ground, under cover and away from sweating walls and other damp surfaces. All bags that have been exposed to water before use should be discarded. Stock of material is to be rotated and used before its expiration date.

## Steel & Concrete Surfaces

Prior to the application of Monokote Z-156T, an inspection should be made to determine that all steel surfaces are acceptable to receive fireproofing. The steel to be fireproofed should be free of oil, grease, excess rolling compounds or lubricants, loose mill scale, excess rust, noncompatible primer, lock down agent or any other substance that will impair proper adhesion. Where necessary, the cleaning of steel surfaces to receive fireproofing will be the responsibility of the general contractor.

Prior to application of Monokote Z-156T, a bonding agent, approved by the fireproofing manufacturer, should be applied to all concrete substrates to receive Monokote Z-156T.

The project architect will determine if the painted/ primed steel to receive fireproofing has been tested to provide the required fire resistance rating.

## Performance Characteristics

PHYSICAL PROPERTIES	RECOMMENDED SPECIFICATIONS	TEST METHOD/NOTES**	LABORATORY TESTED VALUE*
Dry density	Min. 50 pcf (800 kg/m <sup>3</sup> )	ASTM E605	See note below***
Bond strength	Min. 10,000 psf (478 kN/m <sup>2</sup> )	ASTM E736	26,536 psf (1265 kN/m <sup>2</sup> )
Compressive strength @ 10% deformation	850 psi (5.86 MPa)	ASTM E761	1,059 psi (7.3 MPa)
Hardness	40	ASTM D2240	91

Yield	-	Theoretical maximum	13.3 board feet (1.24 m <sup>2</sup> at 25 mm) per bag
Color	-	Natural Concrete Gray	-
Volatile Organic Content (off gassing) at 122 °F (50 °C) organic compounds C6-C28	Less than 1 PPMW (part per million by weight)	Dynamic headspace (Thermal Desorption Gas Chromatography – mass spectrometry)	Less than 1 PPMW (below detectable limits)
Leachable ammonia	Less than 50 PPB– 50 ng/mg	Leachable ion by ion chromatography	Less than 50 PPB (below detectable limits)

\* Independent laboratory tested value. Report available upon request.

\*\* ASTM International test methods modified for bond strength and compressive strength, where required, for high density, high performance products.

\*\*\* All in-place performance tests should be conducted at or below the minimum recommended specification density. Test reports here were conducted at 39.6 pcf (635 kg/m<sup>3</sup>).

## Mixing

Monokote Z-156T should be mixed by machine in a conventional, plaster-type mixer or a continuous mixer specifically modified for cementitious fireproofing. The mixer should be kept clean and free of all previously mixed material. Adjust the mixer speed in a conventional mixer to the lowest speed which gives adequate blending of the material and a mixer density of 65 to 70 pcf (1040 to 1120 kg/m<sup>3</sup>) of material.

Using a suitable metering device and a conventional mixer, add all water to the mixer as the blades turn. Mixing should continue until the mix is lump-free, with a creamy texture. All material is to be thoroughly wet. Overmixing Monokote Z-156T will reduce pumping rate and will negatively affect in-place density and mechanical properties.

## Application

Monokote Z-156T material should not be used if it contains partially set, frozen or caked material.

Monokote Z-156T should have a minimum average dry, in-place density of 50 lbs/ft<sup>3</sup> (800 kg/m<sup>3</sup>).

Monokote Z-156T is formulated to be mixed with water at the job site.

Monokote Z-156T is applied directly to the substrate, at various rates of application which will be job dependent, using standard plastering type equipment or continuous mixer/pump units. A spray gun, with a properly sized orifice and spray shield and air pressure at the nozzle of approximately 20 psi (0.138 MPa), will provide the correct hangability, density and appearance.

**Note:** If freshly sprayed Monokote Z-156T does not adhere properly, it is most likely due to a too wet mix, poor thickness control, or an improperly cleaned substrate.

## Temperature

An air and substrate temperature of 40 °F (4.5 °C) minimum should be maintained for 24 hours prior to application, during application and for a minimum of 72 hours after application of Monokote Z-156T.

## Field Tests

The architect will select an independent testing laboratory (for which the owner will pay) to sample and verify the thickness and density of the fireproofing in accordance with the provisions of ASTM E605-77, *Standard Test Method for Thickness Density of Sprayed Fire-Resistive Material Applied to Structural Members* or Uniform Building Code Standard No. 43-8, *Thickness and Density Determination for Spray Applied Fireproofing*.

**Note:** No recognized field bond strength test procedure exists for sprayed fireproofing materials with bond strengths greater than 1,000 psf (4,882 kg/m<sup>2</sup>) such as Monokote Z-156T. Where bond strength specifications exceed 1,000 psf (4,882 kg/m<sup>2</sup>) it is recommended that independent laboratory test data based upon a modified version of ASTM E736 be submitted to verify specification compliance.

## Safety

Monokote Z-156T is slippery when wet. Signs reading “SLIPPERY WHEN WET” should be posted in all areas in contact with wet fireproofing material. Anti-slip surfaces should be used on all working surfaces.

SDS (Safety Data Sheets) for Monokote Z-156T are available on our web site at [gcpat.com](http://gcpat.com) or call toll free at 866-333-3SBM.

[gcpat.hk](http://gcpat.hk) | For technical information: [asia.enq@gcpat.com](mailto:asia.enq@gcpat.com)

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

Monokote is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2017 GCP Applied Technologies Inc. All rights reserved.

In Canada, 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP (Hong Kong) Ltd., 6 On Chuen Street, On Lok Tsuen Ind Area, Fanling, Hong Kong

This document is only current as of the last updated date stated below and is valid only for use in Hong Kong. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.gcpat.hk](http://www.gcpat.hk). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2022-01-28

[gcpat.hk/solutions/products/monokote-fireproofing/monokote-z-156t](http://gcpat.hk/solutions/products/monokote-fireproofing/monokote-z-156t)